

Product Description	High performance, two packages, epoxy finish, the paint is tough and resistance to wear, kinds of colors.				
Intended Uses	Applied to high build epoxy system, used for surface of cement, steel structures and concretes. The film possesses excellent resistance to weak acid, weak alkali, salt, solvents and their vapours.				
Product Information	Volume Solids	58%			
	Dry Film Thickness	50µm			
	Theoretical Coverage	9.5 m ² /kg			
	Practical Coverage	Allow to appropriate loss factors			
	VOC	363 g/L			
Application Details	Mix ratio	A : B=5 : 1 (By weight)			
	Airless Spray	Recommended: Tip range: 0.43-0.53mm. Fluid pressure: ≥17.6 MPa			
	Brush or Roller	Recommended			
	Conventional Spray	Suitable, But not recommended.			
	Thinner	OUP 103, Suggest adding 3%~5%.			
	Cleaner	OUP 103			
	Pot Life	23°C -6 hours			
	Drying Time	Substrate Temperature	Touch Dry (hours)	Hard Dry (hours)	Over coating Interval
				Minimum	Maximum
	5°C	2	36	36 hours	7 days
	23°C	1	16	16 hours	7 days
	35°C	0.5	12	12 hours	7 days
Storage and Packing	Storage	Store in cool and dry conditions			
	Storage Life	One year			
	Pack Size	A: 20 Kg in 20 liters container; B: 4 Kg in 4 liters container			
	Flash Point	23°C			
	Specific Gravity	Approx 1.22 Kg/L			
Specification and Surface Preparation	<p>New structure: paint right anti-corrosive primer before applying. The surface over the primer is clean, dry and no dirty. Applying this paint within the fixed overcoating interval.</p> <p>Repairing: Treat the corrosive part on the surface, and then paint right primer. The surface of the primer should be clean, dry and no dirty, apply this paint within the fixed overcoating interval.</p>				
Limitations	It can not be fully cured below 5°C . The optimum curing temperature shall be above 10°C . The paint may be chalking after long term outdoor exposure and the degree of chalking depends on the weather. Generally, chalking only happens to a thin layer of surface except in tropical countries.				

Safety Precautions for Solvent Paint

This product should be used in painting area by professional operators. When painting, please refer to Product Data Sheet and MSDS. Consult our company if consumers could not completely understand the precautions for safety and health when applying this product.

This product is a kind of solvent-based paint. In order to avoid danger or accident, minimal safety precautions, as follow, should be done:

The paint contains volatile solvent and is flammable. So must keep away from sparks and open flames. No smoking at application site. Effective precautions (such as using explosion-proof electrical equipments, no static electricity accumulation or metal collision etc) also should be done so as to avoid producing sparks. Flash point of paint, mentioned above on Product Data Sheet, is the lowest temperature at which mixture of the volatile materials of paint can ignite or explode with air, so we suggest painting should be stopped above the temperature of flash point.

Enough ventilation is necessary at application site. In order to remove any danger of explosion, must keep the ratio of gas to air is less than 10%, the minimum explosive limit in general. Therefore, 200m³ of ventilation quantity per 1Kg solvent (according to the solvent) is necessary.

Protect skin and eyes, and avoid touching with paints (Recommend to wear working clothes, gloves, eye protection, face masks, barrier creams and so on). If paint gets in touch with skin, wash fully with a large amount of fresh water and soap or appropriate commercial cleaner. In case of eyes being contaminated, rinse with fresh water for 10min at least and give medical treatment immediately.

Recommend face guard with ventilation pipe for the sake of no absorption of paint fog and harmful solvent gas, especially in badly ventilated conditions.

Handle empty containers with care and do not bring about environmental contamination.

NOTICE: If consumers haven't taken effective safety precautions (Refer to the specifications), our company will NOT be responsible for any accident.

The purpose of the data sheet is to advise you. We can accept no liability for the results obtained during use, due to the variety of applications and the different substrates involved. The publication of the data sheet invalidates all previous data sheets for the product.