

EPE 331 High-Build Epoxy Finish

Product Description	Two packages, a series of colors, semi-gloss or high gloss, high build epoxy anticorrosive paint.					
Intended Uses	The paint is a high performance finish with good resistance to corrosion, chemicals, moistures and oil. Suited for long-term protection of interior surface of tank, pipeline and steel structures that impregnate by underground water.					
Product Information	Volume Solids	75%				
	Dry Film Thickness	120μm equivalent to 160μm wet film.				
	Theoretical Coverage	4.81 m ² /kg				
	Practical Coverage	Allow to appropriate loss factors				
	VOC	215 g/L				
Application Details	Mix ratio	A:B=5:1 (By weight)				
	Airless Spray	Recommended: Tip range: 0.53-0.65mm. Fluid pressure: ≥19.7MPa				
	Brush or Roller	Recommended				
	Conventional Spray	Suitable, But not recommended.				
	Thinner	OUP 103, Suggest adding 3%~5%.				
	Cleaner	OUP 103				
	Pot Life	35°C -2 hours; 23°C -4 hours; 5°C -8 hours				
	Drying Time	Substrate Temperature	Touch Dry (hours)	Hard Dry (hours)	Over coating Interval	
					Minimum	Maximum
		5℃	4	36	36 hours	7 days
		23℃	2	24	24 hours	7 days
		35℃	0.5	18	18 hours	7 days
Storage and Packing	Storage	Store in cool and dry conditions				
	Storage Life	One year				
	Pack Size	A: 20 Kg in 20 liters container; B: 4 Kg in 4 liters container				
	Flash Point	27°C				
	Specific Gravity	Approx 1.30 Kg/L				
Specification and Surface Preparation	Be used for surface painting over the primer or intermediate coating, must keep the surface clean, dry and away from oil, dusty and water.					
Limitations	Preceding coat: Micoceous iron oxide anti-corrosive paint. Epoxy glass flake anti-corrosive paint. Recommended coat: Spray one or two coats with high-pressure airless spray for the sake of reaching 120 microns of dry film thickness.					



Safety Precautions for Solvent Paint

This product should be used in painting area by professional operators. When painting, please refer to Product Data Sheet and MSDS. Consult our company if consumers could not completely understand the precautions for safety and health when applying this product.

This product is a kind of solvent-based paint. In order to avoid danger or accident, minimal safety precautions, as follow, should be done:

The paint contains volatile solvent and is flammable. So must keep away from sparks and open flames. No smoking at application site. Effective precautions (such as using explosion-proof electrical equipments, no static electricity accumulation or metal collision etc) also should be done so as to avoid producing sparks. Flash point of paint, mentioned above on Product Data Sheet, is the lowest temperature at which mixture of the volatile materials of paint can ignite or explode with air, so we suggest painting should be stopped above the temperature of flash point.

Enough ventilation is necessary at application site. In order to remove any danger of explosion, must keep the ratio of gas to air is less than 10%, the minimum explosive limit in general. Therefore, 200m3 of ventilation quantity per 1Kg solvent (according to the solvent) is necessary.

Protect skin and eyes, and avoid touching with paints (Recommend to wear working clothes, gloves, eye protection, face masks, barrier creams and so on). If paint gets in touch with skin, wash fully with a large amount of fresh water and soap or appropriate commercial cleaner. In case of eyes being contaminated, rinse with fresh water for 10min at least and give medical treatment immediately.

Recommend face guard with ventilation pipe for the sake of no absorption of paint fog and harmful solvent gas, especially in badly ventilated conditions.

Handle empty containers with care and do not bring about environmental contamination.

NOTICE: If consumers haven't taken effective safety precautions (Refer to the specifications), our company will NOT be responsible for any accident.

The purpose of the data sheet is to advise you. We can accept no liability for the results obtained during use, due to the variety of applications and the different substrates involved. The publication of the data sheet invalidates all previous data sheets for the product.